TechniCloth® Wipers

Lowest NVR in a nonwoven blended wiper



Features

- » Fiber blend (55% cellulose and 45% polyester)
- Nonwoven, hydroentangled construction with excellent bidirectional strength
- Solvent-safe Bag-Within-A-Bag® cleanroom packaging
- Statistical quality control
- Autoclavable

Benefits

- » Excellent wet and dry strength due to the polyester
- » Highly absorbent due to the cellulose
- » Compatible with most solvents
- Contains no chemical binders
- Low extractable levels



North America 1210 South Park Drive Kernersville, NC 27284 Tel (800) TEXWIPE (336) 996-7046

Fax (336) 996-2297 www.texwipe.com

Asia/Pacific 50 Tagore Lane

Singapore 787494 Tel +65 6468 9433 Fax +65 6468 6772

Europe/Middle East

Saffierlaan 5 2132 VZ Hoofddorp The Netherlands Tel +31 88 1307 400 Fax +31 88 1307 499

Description

TechniCloth® wipers are fabricated from a hydroentangled,nonwoven blend of 55% cellulose and 45% polyester. This fabric blend combines the highly absorbent properties of a natural fiber with the cleanliness and strength of a synthetic wiper. With its low particle counts, low extractable levels and solvent compatibility, TechniCloth® is ideal for general wiping and spill control in controlled environments.

TechniCloth® is also available pre-wetted as a CleanPak® with isopropyl alcohol/deionized water solution.

Applications

- » Designed for general-purpose wiping where economy and cleanliness are of critical importance
- Ideal for applications where high absorbency and low extractables are prime considerations
- Excellent for picking up aqueous spills
- Suitable for cleaning precision components and lab apparatus

Products

	1013	
Number	Description	Packaging
TechniClo	th® Dry Wipers	
TX604	4" x 4" (10 cm x 10 cm) nonwoven, cellulose/polyester- blend wipers	1,200 wipers/bag, 4 inner bags of 300 wipers;10 bags/case
TX606	6" x 6" (15 cm x 15 cm) nonwoven, cellulose/polyester- blend wipers	600 wipers/bag, 2 inner bags of 300 wipers; 10 bags/case
TX609	9" x 9" (23 cm x 23 cm) nonwoven, cellulose/polyester- blend wipers	300 wipers/bag, double bagged; 10 bags/case
TX612	12" x 12" (31 cm x 31 cm) nonwoven, cellulose/polyester- blend wipers	150 wipers/bag, double bagged; 10 bags/case
TechniSa	t® Pre-Wetted	
TX1041	9"x11" (23 cm x 28 cm) wipers, pre-wetted with 70% IPA	70 wipers/reclosable bag; 12 bags/case
TX1045	6"x8" (15 cm x 20 cm) wipers pre-wetted with 70% IPA	100 wipers/canister; 12 canisters/case
TX1048	Gowning Room Wipe™ 8"x5" (20 cm x 13 cm) wipers pre-wetted with 6% IPA	210 wipers/refill; 12 refill packs and 1 fliptop
TX1065	9"x11" (23 cm x 28 cm) wipers pre-wetted with 70% IPA	50 wipers/flexpack; 24 flexpacks/case
TX1067	7"x11" (18 cm x 28 cm) wipers pre-wetted with 70% USP-Grade IPA	200 wipers/reclosable slider bag; 4 slider bags/case
TX8488	9"x11" (23 cm x 28 cm) wipers pre-wetted with 6% IPA	300 wipers/slider bag; 3 bags/case

1, TM18

TX604, TX606, TX609, TX612, TX1041, TX1045, TX1048, TX1065, TX1067, TX8488

TechniCloth® Wipers

Performance Characteristics			
Property	Typical Value	Test Method*	
Basis weight	69 g/m²	1, TM20	
Absorbency Sorptive capacity Sorptive rate	360 mL/m ² <0.3 seconds	1,TM20 1,TM20	
Contamination Chara	cteristics		
Property	Typical Value	Test Method*	
LPC ≥ 0.5 µm	72 x 10 ⁶ particles/m ²	1,TM22	
Particles and Fibers Particles 0.5-5.0 μm 5.0-100 μm Fibers: >100 μm	20 x 10 ⁶ particles/m ² 997,000 particles/m ² 55,000 fibers/m ²	1, 2, TM22 1, 2, TM22 1, 2, TM22	
Nonvolatile Residue IPA extractant DIW extractant	0.01 g/m ² 0.03 g/m ²	1,TM1 1,TM1	
lons Sodium Potassium	34 ppm 1.0 ppm	1, TM18 1, TM18	

Note: The data in this table represent typical analyses of these wipers at the time of publication. These are not specifications. ITW Texwipe continually refines both its processes and its products.

16 ppm

*Test Methods

Chloride

- 1 "Evaluating Wiping Materials Used in Cleanroom and Other Controlled Environments," IEST-RP-CC 004.3, Institute for Environmental Sciences and Technology, Rolling Meadows, IL 2004; www.iest.org.
- 2 "Standard Method for Size-Differentiated Counting of Particles and Fibers Released from Clean Room Wipers Using Optical and Scanning Electron Microscopy," E2090-00, ASTM International, West Conshohocken, PA, 2000; www.astm.org.
- TM Refers to ITW Texwipe Test Method available upon request, contact ITW Texwipe Customer Service at www.texwipe.com for a copy.

ITW Texwipe is the only wiper company to be ISO 9001:2000,13485:2003,14001:2004 and OHSAS 18001:1999 registered.