

# About

The 600mm (24") BioClean Nitramax Glove offer full arm protection and provide comfort, antistatic properties and are resistant to a range of chemicals\*.

## **Specifications**

COMPATIBILITY: ISO Class 4 & EU GMP Grade A

LENGTH:

600mm (24") MATERIAL:

Nitrile

PROTEIN LEVEL: Nitrile contains no natural latex proteins

SURFACE: Textured


SHAPE: Hand specific

COLOUR: White

STERILIZATION: Gamma irradiation

## Features

- Resistant to a range of chemicals\*
- Full arm protection
- Powder-free & latex-free
- Excellent antistatic properties
- Beaded cuff
- Non-particulating EasyTear packaging









# Quality Standards

- Manufactured in a facility holding ISO 9001: 2008 and 89/686/EEC Article 11b certifications
- Conforms to Category 3 Complex Design Personal Protective Equipment PPE Directive 89/686/EEC
- Processed in an NEBB certified ISO Class 4 environment
- Complies with the requirements of Glove Standard EN420:2003 and EN374-1, 2 & 3:2003
- Physical properties comply with European Medical Glove Standard EN455-2:2009
- Sterilized in accordance with ISO 11137-1:2006
- Suitable for contact with all foodstuffs.

# **Physical Properties**

CHARACTERISTICS	VALUE	TEST METHOD
Freedom From Holes	1.5 AQL	EN 374-2:2003
	Performance Level 2	
Glove Length	590/23.2	EN 420:2003
+/-10mm (mm/inches)		
Single Wall Thickness	Cuff: 3.54/0.09	EN 455-2:2009
Minimum (mils/mm)	Palm: 5.91/0.15	
	Finger Tip: 7.09/0.18	
Force At Break During Shelf Life	≥ 9 N	EN 455-2:2009

## Sterilization

Method: Gamma irradiation Minimum Dose: 25kGy Sterility Assurance Level: 10<sup>-6</sup>

## Shelf Life & Storage

Five (5) years from date of manufacture. Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.

PALM WIDTHS (mm) ± 5mm						
SIZE	6.5	7.0	7.5	8.0	8.5	9.0
mm	83	89	95	102	108	114
TES	TEST METHOD			EN 420:2003		

# Glove Cleanliness Characteristics

PARTICLES			TYPICAL PARTICLE COUNT		TEST METHOD			
$\geq 0.5 \mu m (counts/cm^2)$			<2600		IEST-RP-CC005.4			
TYPICAL EXTRACTABLE IONS				TEST METHOD				
ANIONS	Fluoride	Chloride	Nitrite	Bromide	Nitrate	Phosphate	Sulphate	IEST-RP-CC005.4
(µg/cm <sup>2</sup> )	0.001	0.155	ND	ND	0.234	ND	0.119	
CATIONS	Lithium	Sodium	Ammonium	Potassium	Calcium	Magnesium	Zinc	
(µg/cm <sup>2</sup> )	ND	0.014	0.024	0.018	0.704	ND	NT	
ND = Not Detected, NT = Not Tested								





## TO ORDER

Re-order code	Size
BNMS-65	6.5
BNMS-70	7.0
BNMS-75	7.5
BNMS-80	8.0
BNMS-85	8.5
BNMS-90	9.0

#### Packing

One pair per inner PE wallet; one wallet per sealed EasyTear PE pouch; 10 pouches per sealed outer PE bag; 10 outer bags per lined carton (100 pairs)

#### For additional information visit us at www.bioclean.com, or call us at +44 1638 663338

Nitritex Ltd Minton Enterprise Park Oaks Drive Newmarket, Suffolk CB8 7YY United Kingdom



BNMS/1806/PDS24

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

\*Warning: No glove provides complete protection against all chemicals. Users must test the gloves against the particular chemicals and environment in which they will be used.

\*\*Please see product validation pack or contact Ansell customer service for specific data on use of gloves with cytotoxic drugs. Gloves used for protection against such drugs must be selected specifically for the type of chemicals used.

Ansell, (6) and TM are trademarks owned by Ansell Limited or one of its affiliates. (2012 - 2018 Ansell Limited. All Rights Reserved.